

# SYNOCURE<sup>®</sup> 9279 S 65

PROTECTIVE & MARINE COATINGS

(FORMERLY E 20779)

**Product Application details** SYNOCURE<sup>®</sup> 9279 S 65 is a hydroxy functional acrylic designed to crosslink at room temperature or under low-bake conditions with aliphatic polyisocyanates. It is particularly recommended for use in vehicle refinishing, A.C.E., Transport coatings and Heavy Duty Coatings.

**Performance Benefits**

- Fast dry and good early hardness
- Good application properties
- Excellent mechanical properties
- Good weathering performance

**Polymer Type**

- Solventborne Acrylic

<b>Sales Specifications</b>	Solid Content at 125°C, % (ISO 3251)	64 - 66
	Viscosity at 25°C, mPa.s (ISO 3219)	1500 - 3000
	Colour, Hazen scale (ISO 6271)	100 max
	Acid value, mg KOH/g (ISO 2114)	10 max

<b>Other Characteristics<sup>1</sup></b>	Volatile	Butyl acetate / Xylene (3 : 1)
	Flash point, °C (ISO 3679)	25
	Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.01
	Hydroxyl Content, %	4.2
	Hydroxyl Equivalent weight	400

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

<sup>1</sup> The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### RECOMMENDATIONS FOR USE

SYNOCURE<sup>®</sup> 9279 S 65 should be mixed with the selected polyisocyanate just prior to application. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Tolonate HDB 75 MX (1), the recommended ratios would be:

	on solid resin	as supplied
SYNOCURE <sup>®</sup> 9279 S 65	400	615
Tolonate HDB 75 MX (1)	191	255

### Formulation Guidelines

---

### SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 9279 S 65 used should be free from water and not contain groups that react with isocyanates. Esters and ketones are true solvents and are recommended for use in combination with aromatic hydrocarbon diluents such as xylene.

Notes: (1) *Perstorp*

---

### **Product Safety**

Please refer to the corresponding Safety Data Sheet.

---

### **Storage & Handling**

SYNOCURE® 9279 S 65 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. Under the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date.

---

The information contained in this document is based on trials carried out by our Technical centres and data selected from literature, but shall in no event be held or constitute or imply any warranty or undertaking, expressed or implied, or commitment on our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



Arkema Coating Resins  
420, rue d'Estienne d'Orves  
F-92705 – Colombes Cedex – France  
[www.arkema.com](http://www.arkema.com)