

SYNOCURE® 867 BA 60

GENERAL INDUSTRY

Product Application details SYNOCURE® 867 BA 60 is a hydroxy functional acrylic designed to crosslink at room temperature with polyisocyanates. SYNOCURE® 867 BA 60 is especially recommended for coatings where outdoor durability and resistant properties are of prime importance.

- Performance Benefits**
- Excellent chemical and stain resistance
 - Good durability
 - Excellent adhesion
 - Long pot life

Polymer Type •Solventborne Acrylic

Sales Specifications	Solid Content at 125°C, % (ISO 3251)	58 - 62
	Viscosity at 25°C, mPa.s (DIN 53 015)	3500 - 6000
	Colour, Pt/Co Scale (DIN EN 1557)	70 max
	Acid value, mg KOH/g (ISO 2114)	8 max

Other Characteristics¹	Volatile	Butyl acetate
	Flash point, °C (ISO 3679)	24
	Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.02
	Hydroxyl Content, %	2.8
	Hydroxyl Equivalent weight	600

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOCURE® 867 BA 60 should be mixed with the selected polyisocyanate just prior to application. The mixing ratio is not critical, although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Desmodur® N 75 series (1) or Tolonate® HDB 75 MX (2), the recommended ratios would be:

	on solid resin	as supplied
SYNOCURE® 867 BA 60	600	1000
Desmodur® N 75 series (1) or Tolonate® HDB 75 MX (2)	191	255

Formulation Guidelines

When mixed with polyisocyanates in stoichiometric proportions, SYNOCURE[®] 867 BA 60 has a pot life in excess of 8 hours at temperatures from 15°C to 30°C. This usable period will be reduced in high temperature conditions or when catalysts are used.

The initial curing rate can be increased by the use of tin or zinc catalysts such as dibutyl tin dilaurate or zinc octoate. The levels used will depend on the specific requirements, but typical metal contents calculated on total solid resin are 0.001% tin and 0.0015% zinc.

Coatings prepared from SYNOCURE[®] 867 BA 60 and stoichiometric quantities of polyisocyanates will have sand dry times of approximately 15min and hard dry times of 1h.

SOLUBILITY

Solvents used in systems containing SYNOCURE[®] 867 BA 60 should be low water content grades and not contain chemical groups (such as hydroxyl) which will react with isocyanates and thereby inhibit the film forming reaction. Esters and ketones are true solvents for this type of system, usually combined with aromatic hydrocarbon diluents.

(1) BayerMaterialScience, (2) Perstorp

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOCURE[®] 867 BA 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C.

Exposure to direct sunlight should be avoided.

Under the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date.

The information contained in this document is based on trials carried out by our Technical centres and data selected from literature, but shall in no event be held or constitute or imply any warranty or undertaking, expressed or implied, or commitment on our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by ARKEMA with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



Arkema Coating Resins
420, rue d'Estienne d'Orves
F-92705 – Colombes Cedex – France
www.arkema.com