



Chemical composition

Propoxyated ethoxylated linear alcohol
Concentration > 99 %

Physical and Chemical Properties

Polarity: nonionic
Density (20 °C): 0.99 g/cm³
Boiling point: 200 °C
Flash point: >100 °C (closed cup)
Viscosity (25 °C): 142 mPa.s

Application

Low foaming surfactant for brazing flux suspensions (up to 50 °C)
Recommended concentration:
0.1 to 0.2 %

Specification

Appearance at 25 °C: clear to slightly hazy liquid
Colour (Gardner): max. 3
Water (K. Fischer): 0.5 %
Cloud point at 1%: 25 – 29 °C
pH 10% (in water): 6 – 8

Packaging

Plastic canister.
5, 10, 20 kg net weight.

5 kg canister

Height 228 mm
Width 194 mm
Depth 168 mm
Filling weight 5.0 kg
Gross weight 5.35 kg



10 kg canister

Height 330 mm
Width 230 mm
Depth 190 mm
Filling weight 10.0 kg
Gross weight 11.0 kg

CP3-pallet with 10 kg canister

Units 28 per layer
Height 520 mm
Width 1,140 mm
Depth 1,140 mm
Gross weight 330 kg per layer



Storage, Handling

Product should be stored in dedicated areas prior to use.

If stored in original packaging, shelf life is 2 years.

Classification

Products are classified as hazardous according to the European regulation (EC) 1272/2008 (GHS)

Detailed information can be found in the relevant Safety Data Sheet (SDS).

MANAGEMENT SYSTEM

DQS – certified according

ISO 9001 : 2015
ISO 14001 : 2015
ISO 50001 : 2018
ISO 45001 : 2018

NOCOLOK® is registered trademark of Solvay Fluor GmbH, Germany

Solvay Flux GmbH

Dieselstraße 26
30827 Garbsen, Germany

www.nocolok.com

Phone: +49 511 857-0
Mail: info.flux@solvay.com

www.solvay.com

SOLVAY